

Primacrete Grip.

Aggregate primer for all types of surfaces.



Uses

As a primer based on acrylic resins in aqueous dispersion and inerts of siliceous nature, used as a bonding bridge between all types of surfaces and microcement.

Technical information

PROPERTIES	SPECIFICATION	UNIT	METHOD
Nature	Acrylic emulsion and aggregate		
pH	7,5-9		UNE-EN ISO 19396-1:2020
Density	1,50±0,05	g/cm ³	UNE-EN ISO 2811-1
Viscosity at 23°C Comp. A	5000±1000	mPa-s	EN ISO 3219
Non-volatile content	61-63	%	UNE-EN ISO 3251:2020
Performance	5-3	m ² /Kg	
VOC:2024/42/IIA(g)(30)Max. VOCs	<1	g/L	
Drying time to touch	2-3	hours	

Application

The substrates must be clean and free of grease, oils, oxides, debris and loose or poorly adhered parts. Apply to the surface by brush or roller. Cover the entire surface, trying to apply a uniform film. The application temperature should be between 5 -30° C. Wait approximately 2-3 hours (depending on the environmental conditions and the absorption of the substrate) to apply the microcement.

Special precautions

It is essential to follow the instructions on the container label. For further information, please refer to the product safety data sheet. Empty containers must be disposed of in accordance with current legislation.

Storage

It should be stored in its original closed container and protected from the weather at temperatures between 10°C and 30°C, in a dry and well ventilated place, away from sources of heat and direct sunlight. The shelf life is 1 year from the date of manufacture, if stored properly.

Storage

The product should be stored in its original closed container and protected from the weather at temperatures between 10°C and 30°C, in a dry and well ventilated place, away from sources of heat and direct sunlight. The shelf life is 1 year from the date of manufacture, if stored properly.

Cleaning of tools

The tools are washed with universal solvent immediately after use.

Presentation

Available in 5 kg packs