

Primacrete Grip.

Ready-to-use primer with aggregate, for interior and exterior use, without emission of volatile organic substances, based on synthetic resins in aqueous dispersion.



Technical data

- Polymer type: Acrylic
- Appearance: Milky granular liquid
- pH: Between 7,5 and 9
- Apparent density: $1,5 \pm 0,05 \text{ g/cm}^3$
- Dry to touch: 3/4 h, depending on applied thickness and environmental conditions

Properties

- It provides a rough surface ensuring excellent adhesion on smooth or low absorption substrates.
- It is used for the application of micro-cement, plaster, tile installation on concrete, ceramic, hydraulic tiles...
- It can be applied by roller or brush in a single coat.
- The product is supplied ready for use.

Recommendations of use

The substrate must be dry, clean and firm, free of grease or oil. Shake the container well before use and apply Primacrete GRIP on the surface by brush or roller. Between 15 and 30 minutes, depending on the environmental conditions and the absorption of the support, it is possible to proceed with the application of the plaster, plastering, etc., later.

Special precautions

In case of contact with eyes, rinse with plenty of water for 15 minutes.
In case of contact with skin wash with soap and water.
Do not swallow. In case of ingestion do not induce vomiting and seek medical attention immediately. Do not dilute with water.

It is recommended to comply with the following measures:

- Good ventilation.
- Protective goggles to avoid splashing.
- Rubber gloves.

Empty containers should be disposed of in accordance with current legal regulations. To prevent the product from drying out or thickening, close the lid after each use. This product is not toxic, dangerous or flammable, under normal handling conditions. This product does not contain harmful substances that would require, under current regulations, any additional labeling measures. Keep out of the reach of children

Consumption

Performance for Primacrete Grip:

- 0.25 kg/m^2

Characteristics

- Aliphatic polyurethane dispersion with polycarbonate
- Solids: $22 \pm 2\%$

Packaging

Available in 5 kg containers.

Storage

It should be stored in its original closed container and protected from the weather at temperatures between 10°C and 30°C, in a dry and well ventilated place, away from heat sources and direct sunlight. The shelf life is 1 year from the date of manufacture, if stored properly.

Cleaning of tools

The tools are washed with water, immediately after use.